

ACI Footing Barrier: PHYSICAL PROPERTIES

Colour	Gray
Elongation (ASTM D412)	1400%
Low Temperature Flexibility	Flexible to -29°C (-20°F)
Asphalt Content	0.0%
180 Degree Peel Adhesion	8 kg per 2.54 cm (18 lbs per inch)
Liquid Water Absorption (ASTM D95)	Less than 0.5%
Resistance to Bacteria ASTM D4299-83 (modified)	No Attack
Resistance to Degradation in Soil ASTM E154 (soil preparation)	Excellent
Resistance to Algae ASTM G2975 (modified)	No Attack
Resistance to Fungus ASTM D2020 (modified)	No Attack